

Selectietabel 1-component RTV

Type:	Kleur:	Uithardings- systeem:	Huidvorming (min.)	Viscositeit:	Hardheid (°ShA)
Silicone RTV102/-3/-6/-8/-9	Diverse	Acetoxy	20	Pasta	30
Silicone RTV112/-6/-8	Diverse	Acetoxy	20-30	Semi Flowable	20-25
Silicone RTV157/-9	Grijs/Rood	Acetoxy	45	Pasta	28
Silicone IS802/-03/-08E	Wit/Zwart/Transl.	Acetoxy	25	Pasta	20
Silicone IS5128E	Translucent	Acetoxy	10	Pasta	20
Silicone IS5675	Glashelder	Acetoxy	5	Pasta	25
Silicone RTV160/-2	Wit	Alkoxy	240	Semi Flowable	25/35
Silicone RTV167	Grijs	Alkoxy	240	Pasta	37
Silicone TSE392	Helder/Wit	Alkoxy	5	Pasta	30
Silicone TSE397	Helder/Wit	Alkoxy	10	Semi Flowable	20
Silicone TSE399	Helder/Wit/Zwart	Alkoxy	10	Flowable	30
Silicone RTV5242/-3/-9	Diverse	Alkoxy	45	Pasta	40
Silicone TSE325	Wit	Additie *	n.v.t.	Flowable	12
Silicone TSE326	Roodbruin	Additie *	n.v.t.	Semi Flowable	43

*) Versnelde uitharding bij verhoogde temperatuur