

## TSE3062

### Description

TSE3062 is a two-component, low viscosity silicone gel designed for electronics potting applications. This product cures at room temperature to a soft, tacky gel with the addition of curing agent. The cure time can be accelerated with heat. The soft nature and cushioning effect of this product provides excellent protection for electronic assemblies from external humidity, mechanical shock and vibration.

### Key Features and Typical Benefits

- Convenient 1:1 mix ratio by weight
- Low viscosity - easily pourable
- Room temperature curable and heat accelerated cure
- Soft, tacky gel
- Absorbs shock and protects delicate mechanical components from vibration
- No reactive by-products; non corrosive
- Excellent electrical properties
- Excellent resistance to temperature extremes

### Typical Physical Properties

Uncured Properties		TSE3062 (A)	TSE3062 (B)
Appearance		Transparent	
Viscosity (23 °C)	Pa·s	1.0	1.0
After mixing	Pa·s	1.0	
Mix ratio by weight		1:1	
Work life (23 °C)	h	1	
Density	g/cm <sup>3</sup>	0.97	
<b>Cured Properties (0.5h at 70 °C)</b>			

Appearance		Gel
Penetration		55
Volume resistivity	$\Omega \cdot \text{cm}$	$1.0 \times 10^{15}$
Dielectric strength	kV/mm	18
Dielectric constant (60Hz)		2.7
Dielectric loss (60Hz)		0.001
Volume expansion	1/K	$1 \times 10^{-3}$
Thermal conductivity	W/m·K	0.17

Typical physical properties are average data and should not be used as or to develop product specifications.

### Potential Applications

- Electrical and electronic potting such as hybrid IC and power module
- Potting of high voltage parts

### Processing Recommendations

Materials such as water, sulphur, nitrogen compounds, organic metallic salts, phosphorus compounds, etc. contained in the surface of the substrate can inhibit curing. A sample patch should always be conducted before proceeding to determine compatibility. All parts should be clean and dry prior to applications.

### Availability

TSE3062 is available as 2kg, 36kg, and 360kg kits.

### General Considerations for Use

While the typical operating temperature for silicone materials ranges from  $-45^{\circ}\text{C}$  to  $200^{\circ}\text{C}$ , the long-term maintenance of its initial properties is dependent upon design related stress considerations, substrate materials, frequency of thermal cycles, and other factors.

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any

invention covered by any patent, without authority from the owner of the patent.

### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### **Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### **Contact Information**

For product prices, availability, or order placement, contact our customer service at [Momentive.com/CustomerService/](http://Momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### **DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS**

**AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**